

Ferromagnetic Resonance Force Microscopy on Microscopic Cobalt Single Layer Films

Z. Zhang* and P. C. Hammel†

Los Alamos National Laboratory, Los Alamos, NM 87545

M. Midzor and M. L. Roukes

California Institute of Technology, Pasadena, CA 91125

J. R. Childress‡

University of Florida, Gainesville, FL 32611

We report mechanical detection of ferromagnetic resonance signals from microscopic Co single layer thin films using a magnetic resonance force microscope (MRFM). Variations in the magnetic anisotropy field and the inhomogeneity of were clearly observed in the FMR spectra of microscopic Co thin films 500 and 1000 Å thick and $\sim 40 \times 200 \mu\text{m}^2$ in lateral extent. This demonstrates the important potential that MRFM detection of FMR holds for microscopic characterization of spatial distribution of magnetic properties in magnetic layered materials and devices.

PACS numbers: 76.30.-v, 76.90.+d

Ferromagnetic resonance (FMR) is an important tool for characterizing magnetic materials [1,2]. It has played a particularly important role in studies of the magnetic multilayer systems which are becoming widely used in the recording industry as recording read heads and/or media where it has been used to measure the dependence of the interlayer exchange coupling on the thickness of the spacer layer. The ability to perform microscopic FMR would be extremely valuable, enabling characterization, on a microscopic scale, of distributions of magnetic anisotropy and exchange energies in magnetic devices. Microscopic FMR cannot be performed using conventional techniques for two reasons. First, the sensitivity of conventional FMR is inadequate; for most magnetic thin films, such as Co and Fe, sample areas on the order of $(\text{mm})^2$ are needed in order to obtain sufficient signal at X-band. Second, conventional FMR is performed in a uniform magnetic field so there is no means to identify the spatial origin of a particular contribution to the FMR signal.

We have recently demonstrated the feasibility of microscopic FMR [3] by means of the highly sensitive magnetic resonance force microscope (MRFM) [4,5]. The MRFM mechanically detects the resonance signal by sensitively detecting the oscillatory response of a micro-mechanical resonator [6,7]. Even before optimizing the instrument, the excellent force sensitivity of the MRFM has enabled detection of ferromagnetic resonance signals from magnetic thin films only tens of microns in lateral extent [3]. As in magnetic resonance imaging, the MRFM experiment is performed in a strong field gradient; this allows the MRFM to confine the excitation of spin precession to a well defined surface of constant magnetic field (or “sensitive slice”) where the magnetic resonance condition is met. Spatially resolved microscopy is achieved by scanning this sensitive slice through the sample [8,9].

In our previous demonstration of microscopic FMR using the MRFM, a single crystal yttrium iron garnet

(YIG) thin film was used [3]. YIG was chosen because it has very strong FMR intensity and narrow resonance linewidth (< 1 Gauss). However, typical magnetic devices are composed of metallic ferromagnets such as Co and Fe. These have much larger FMR linewidths (of order 100 Gauss) and hence weaker signals, making the signals harder to detect. It is also essential that the resonant field be substantially larger than the linewidth, hence that the irradiation frequency exceed ~ 2 –3 GHz. Here we report successful detection of the FMR signal from a microscopic, single layer Co thin film by means of an MRFM instrument. Irradiation at high frequency (~ 8 GHz here) and implementation of a novel MRFM geometry, the perpendicular geometry, as described immediately below were essential features of the experiment.

The MRFM apparatus used in this work has been described earlier in Refs. [3] and [9]. The polycrystalline Co films were deposited onto the tip of the single crystal Si cantilever over polycrystalline Ag underlayers; the films were capped with protective Ag films. The sizes and locations of the films were determined by a simple mask. Results from three samples will be presented. Sample 1, 1000 Å thick, was sputter deposited at a substrate temperature $< 50^\circ\text{C}$ onto a 30 Å Ag layer. Samples 2 (1000 Å) and 3 (500 Å) were thermally evaporated onto 50 Å Ag layers. A $\text{Nd}_2\text{Fe}_{14}\text{B}$ bar magnet (~ 6.4 mm in diameter and ~ 6.4 mm long) was used to generate the field gradient $\nabla\mathbf{B}$, and therefore a force \mathbf{F} on the cantilever:

$$F_x = m_x \frac{\partial B_x^{\text{bar}}}{\partial x} + m_z \frac{\partial B_x^{\text{bar}}}{\partial z}, \quad (1)$$

where the oscillatory displacement of the cantilever is parallel to the x -axis, and the axis of the bar magnet is parallel to the z -axis. The components of the magnetic moment of the Co film along these axes are represented by m_x and m_z .

For these measurements the earlier apparatus was modified in two respects: we employed a geometry in

FIG. 2. Dependence of the resonance field on the angle ϕ_H between the applied magnetic field and the film plane for the sputtered sample. The solid line is a theoretical fit from a classical FMR theory with $g = 2.18$ and $4\pi M_{\text{eff}} = 17.6 \text{ kG}$. A vanishing crystalline anisotropy field was assumed in the calculation. The inset shows a schematic diagram of the MRFM apparatus.

gradient $\partial B_{\text{total}}/\partial z$ due to the bar magnet at the Co sample is $\sim 0.15 \text{ G}/\mu\text{m}$. For our Co film, which is $\sim 200 \mu\text{m}$ long, this corresponds to a 30 Gauss field difference across the film. Because the resonance linewidth of the Co films (between 50 and 100 G) is greater than this, we are not able to distinguish resonance signals arising from different spatial locations in the microscopic Co film by means of the applied field gradient. The larger field gradient produced by reducing the diameter of the magnet will be necessary to improve the spatial resolution of the experiment.

Analysis of our FMR spectra enable us to determine magnetic properties of the microscopic ferromagnetic films; in particular, these spectra reveal the dependence of the magnetic anisotropy and the film quality on the deposition method and film thickness. The magnetic anisotropy of the sputtered film was determined by analysis of the dependence of the resonance field on ϕ_H . This angle is varied by displacing the Co film with respect to the bar magnet in either the x or z direction, thus changing the x and z components of the magnetic field applied to the film. This result is shown in Fig. 2. The solid curve in Fig. 2 is a theoretical prediction for this dependence from classical FMR theory assuming only a demagnetization field. In particular, no crystalline anisotropy is observed; this absence is an expected consequence of the polycrystalline nature of the film. As shown, excellent agreement was obtained.

Fig. 1 shows the FMR spectra of the three films taken at constant angle $\phi_H \simeq 33^\circ$. The resonant field position is larger in evaporated films indicating an additional anisotropy in these films. In particular, the effective demagnetization field, $4\pi M_{\text{eff}} = 4\pi M_s - 2K_u/M_s$ is different (where K_u is the uniaxial anisotropy energy density perpendicular to the film plane). This variation in K_u could arise from different residual stresses developed during the film deposition. Assuming that the saturation magnetization M_s for each of the Co films is the same as for bulk Co ($\sim 1400 \text{ emu}/\text{cm}^3$), we find that $2K_u/M_s \sim 0$ for the sputtered film, $\sim 2.8 \text{ kG}$ for the 1000 \AA evaporated film, and $\sim 4.9 \text{ kG}$ for the 500 \AA evaporated film. These results indicate that the evaporated samples develop larger stress than the sputtered sample, and that the stress decreases with increasing film thickness.

A dependence of sample homogeneity on deposition process is also evident in Fig. 1 from the variation of the FMR linewidth. The sputtered sample has the narrowest linewidth, about 45 G. The applied field gradient cannot explain this linewidth variation because the sputtered sample has the largest spatial extent along the z -axis (the direction along which the field gradient is largest). Thus, the linewidth reflects the quality or homogeneity of the Co film itself, and these measurement indicate that sputtering produces a more homogeneous film than does thermal evaporation. Between the two evaporated samples, the 500 \AA sample has the narrower resonance linewidth, possibly because a two stage evaporation was required for the 1000 \AA film, or possibly indicating that the film

quality degrades as it becomes thicker.

In conclusion, an MRFM has been successfully used to detect FMR signals from microscopic Co single layer thin films with unprecedented sensitivity. These signals were obtained from a perpendicular-geometry MRFM operating at a frequency of 8 GHz. These conditions ensured that, for modest resonance fields, the applied field component in the plane of the film was sufficient to saturate the film. The large signal intensity indicates that the sensitivity of the current MRFM is adequate to detect FMR signals from microscopic metallic ferromagnets as thin as 20 \AA . In fact, this has been verified in our most recent experiments on 50 \AA Co films [13]. Although the field gradient in the present instrument is not large enough to distinguish FMR signals from different spatial locations in the film, our results demonstrate that MRFM detection of FMR has the sensitivity to enable microscopic studies of systems composed of thin film metallic ferromagnets. We have demonstrated, in particular, the ability to observe variations in magnetic anisotropy energy and film quality from one microscopic sample to another. In order to improve the spatial resolution, larger field gradients from smaller bar magnets are needed. Placing the magnetic probe on the cantilever is an essential step to enable experiments on samples prepared on well characterized substrates. These improvements are presently underway.

We gratefully acknowledge fruitful discussions with Philip Wigen at Ohio State University and the support of the Center for Nonlinear Studies at Los Alamos National Laboratory. Work at Los Alamos supported by the United States Department of Energy, Office of Basic Energy Sciences.

* Present address: Seagate Technology, Mailstop 5-601, 3061 Zanker Road, San Jose, CA 95134.

† To whom correspondence should be addressed; e-mail: pch@lanl.gov.

‡ Present address: IBM Almaden Research Center, San Jose, CA 95120.

- [1] P. E. Wigen, in *Magnetic Multilayers*, edited by L. H. Bennett and R. E. Watson (World Scientific Publishing Co. Pte. Ltd., Singapore, 1994), pp. 183–226.
- [2] B. Heinrich, in *Ultrathin Magnetic Structures II*, edited by B. Heinrich and J. A. C. Bland (Springer-Verlag, Berlin Heidelberg, 1994), pp. 195–222.
- [3] Z. Zhang, P. C. Hammel, and P. E. Wigen, *Appl. Phys. Lett.* **68**, 2005 (1996).
- [4] D. Rugar, C. S. Yannoni, and J. A. Sidles, *Nature* **360**, 563 (1992).
- [5] D. Rugar, O. Züger, S. T. Hoen, C. S. Yannoni, H.-M. Vieth and R. D. Kendrick, *Science* **264**, 1560 (1994).
- [6] J. A. Sidles, *Appl. Phys. Lett.* **58**, 2854 (1991).
- [7] J. A. Sidles, *Phys. Rev. Lett.* **68**, 1124 (1992).

- [8] O. Züger and D. Rugar, J. Appl. Phys. **75**, 6211 (1994).
- [9] P. C. Hammel, Z. Zhang, G. J. Moore, and M. L. Roukes, J. Low Temp. Phys. **101**, 59 (1995).
- [10] W. J. Wallace and R. H. Silsbee, Rev. Sci. Instr. **62**, 1754 (1991).
- [11] K. Wago, O. Züger, J. Wegener, R. Kendrick, C. S. Yannoni and D. Rugar, Rev. Sci. Instrum. **68**, 1823 (1997).
- [12] K. J. Bruland, J. Krzystek, J. L. Garbini, and J. A. Sidles, Rev. Sci. Instr. **66**, 2853 (1995).
- [13] M. Midzor, M. L. Roukes, B. J. Suh, Z. Zhang, P. C. Hammel and J. R. Childress, unpublished.